

TECHNICAL DATA SHEET

RCF™ High Strength Anchoring Epoxy Paste | Revision Date 7/25/2019

1633 Thornwood Dr.
Heath, OH 43056 USA
P: +1 888 684 3889
E: info@rhinocarbonfiber.com

01

1. DESCRIPTION

RCF™ High Strength Anchoring Epoxy Paste is a two-component, 100% solids, moisture-insensitive, high strength, high modulus, multi-purpose liquid epoxy gel adhesive. It meets the current ASTM C881 and AASHTO M235 Types I, II, IV & V Grade 3, Classes B & C specifications. It has passed 4 million cycles of simulated seismic tension test.

2. WHERE TO USE

Use as an adhesive for setting/bonding subsurface or external reinforcements to concrete masonry or other substrates. Can also be used for reinforcing steel dowels, threaded rods, bolts, and inserts into existing concrete. Use as a multipurpose bond adhesive for structural bonding fresh or hardened concrete to hardened concrete, sealing cracks, setting injection ports prior to injection grouting, and as a pick-proof sealant.

3. ADVANTAGES

- Moisture tolerant
- High strength, high modulus structural adhesive
- Made in America
- Convenient 1:1 mix ratio by volume
- Rapid cure formula
- Agency Independent testing lab certification
- Solvent free
- No-sag gel consistency

4. SHELF LIFE / STORAGE

24 month shelf life when stored in unopened containers in dry conditions and stored at 40°F-95°F (4°C-35°C)

5. TECHNICAL DATA

RCF™ High Strength Anchoring Epoxy Paste Technical Data	
Storage Conditions:	40°F – 95°F (5°C – 35°C).
Condition material to:	65°F – 85°F (18°C – 29°C) before using.
Mix Ratio	1:1 by volume
Viscosity	¼ inch no-sag gel
Gel Time (60 g mass)	10 minutes
Tack Free Time (73°F or 23°C)	2 to 3 hours
Tensile Properties (ASTM D638), 7 day cure	
Tensile Strength:	7,500 psi (51.7 MPa)
Tensile Elongation:	1.2%
Bond Strength (ASTM C882)	
1 day cure:	2,000 psi (13.8 MPa)
7 day cure:	2,500 psi (17.2 MPa)
Compressive Properties (ASTM D695), 7 day cure	
Compressive Strength:	12,500 psi (86.2 MPa)
Compressive Modulus:	300,000 psi (2,070 MPa)
Shear Strength (ASTM D732)	2,800 psi (19.3 MPa)
Shrinkage on Cure (ASTM D2566)	0.001
Thermal Compatibility (ASTM C884)	Pass
Heat Deflection Temperature (ASTM D648)	140°F (60°C)
Water Absorption (ASTM D570)	0.1% (24 hr)

*NOTE: Epoxy cure is affected by temperature. Low Temperatures will increase cure time, higher temperatures with decrease cure time.

6. CONDITION PRODUCT

Condition cartridge and contents to a temperature of 65°F to 95°F (18°C - 35°C) for easier dispensing.

7. LIMITATIONS & WARNINGS

Minimum substrate temperature is 40°F (5°C). Do not thin. Solvents will prevent proper cure.

8. MANUFACTURER'S PRINTED INSTALLATION INSTRUCTIONS

For complete installation instructions on various applications using RCF™ High Strength Anchoring Epoxy Paste visit www.rhinocarbonfiber.com or call Rhino Products for more information at 1-888-684-3889.

9. SURFACE PREPARATION

RCF™ High Strength Anchoring Epoxy Paste is an ideal bonding agent for multiple surfaces including concrete, brick, stone, block, and metal. Surfaces must be clean and profiled or textured. New concrete must be a minimum of 28 days old. All dirt, oil, debris, wax, grease or dust must be removed. Prepare the surface mechanically using a scarifier, sandblast, shot blast, bush hammer or other equipment that will give the surface profile needed for the application. A roughened surface that exposes the aggregate and/or pores of the substrate is imperative for good adhesion.

10. CLEAN UP

Clean tools and equipment with Rhino Carbon Fiber™ Tough Wipes, a biodegradable formula that removes and neutralizes the epoxy. Do not allow epoxy to harden on equipment as cured material can only be removed mechanically.

11. SAFETY

Please refer to the SDS for RCF™ High Strength Anchoring Epoxy Paste published on our Website, www.rhinocarbonfiber.com or call Rhino Products for more information at 1-888-684-3889. This TDS sheet is not intended to list all Safety and Health Requirements necessary for the installation of these products. All Health and Safety Requirements required by OSHA shall be followed.

12. WARRANTY

Rhino Products warrants to the Buyer that this product is in good quality and conforms to the manufacturer's specifications in force on the date of manufacture and when used in accordance with the Installation Instructions and when stored as directed in the technical literature.

Manufacturer cannot warrant or guarantee any particular method of use, performance or application under any particular condition and Buyer is responsible for determining the suitability of intended purpose and assumes all risks therein. RCF™ shall not be liable for any injury, loss, cost of labor or consequential damages either directly, indirectly or incidentally, arising out of the use or misuse of any product sold by RCF™ or another distributor. If the product is proven to be in non-conformance, the Buyers sole remedy shall be a refund of the purchase price or replacement of product.